

GEOTEX® 2x2UF is a woven polypropylene geotextile containing high-tenacity filaments and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. These characteristics make GEOTEX® 2x2UF ideal for roadway reinforcement and subgrade stabilization, runway and railway construction, embankment stabilization, MSE walls and other environmental applications. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 2x2UF conforms to the property values listed below¹. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

| PROPERTY | TEST METHOD | MARV ² | |
|--|-------------|------------------------|---------------------------|
| | | ENGLISH | METRIC |
| ORIGIN OF MATERIALS | | | |
| % U.S. Manufactured | | 100% | 100% |
| MECHANICAL | | | |
| Wide Width Tensile at 2% Strain | ASTM D-4595 | 600 x 600 lbs/ft | 8.8 x 8.8 kN/m |
| Wide Width Tensile at 5% Strain | ASTM D-4595 | 1620 x 1620 lbs/ft | 23.6 x 23.6 kN/m |
| ENDURANCE | | | |
| UV Resistance at 500 hrs | ASTM D-4355 | 90% | 90% |
| Factory Seam Strength | ASTM D-4844 | 2400 lbs/ft | 35 kN/m |
| HYDRAULIC | | | |
| Apparent Opening Size (AOS) ³ | ASTM D-4751 | 40 US Std. Sieve | 0.425 mm |
| Permittivity | ASTM D-4491 | 0.9 sec-1 | 0.9 sec-1 |
| Water Flow Rate | ASTM D-4491 | 70 gpm/ft ² | 2852 l/min/m ² |
| ROLL SIZES ⁴ | | 15.0 ft x 300 ft | 4.57 m x 91.5 m |

NOTES:

1. The property values listed above are effective 12/17/2018 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Values represent testing at time of manufacture.
3. Maximum average roll value.
4. Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.

ENGINEERED EARTH SOLUTIONS™

www.propexglobal.com



Propex Operating Company, LLC · 4019 Industry Drive Chattanooga, TN 37416 · ph 800 621 1273 · ph 423 855 1466

ARMORMAX®, PYRAMAT®, LANDLOK®, X3®, PYRAWALL®, SCOURLOK®, GEOTEX®, PETROMAT®, PETROTAC®, REFLECTEX®, and GRIDPRO™ are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.