

GEOTEX® 350ST is a woven polypropylene geotextile containing heavy woven tape/fibrillated yarns and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. These characteristics make GEOTEX® 350ST ideal for the construction of embankments over soft soils, steepened slopes, and modular block and/or wrapped-face retaining walls. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 350ST conforms to the property values listed below<sup>1</sup>. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP tested for AASHTO standards.

MARV <sup>2</sup>			
PROPERTY	TEST METHOD	ENGLISH	METRIC
<b>MECHANICAL</b>			
Grab Tensile Strength	ASTM D-4632	350 x 350 lbs	1557 x 1557 N
Grab Elongation (Maximum)	ASTM D-4632	25 x 25 %	25 x 25 %
CBR Puncture	ASTM D-6241	1000 lbs	4448 N
Trapezoidal Tear	ASTM D-4533	100 lbs	445 N
<b>ENDURANCE</b>			
UV Resistance at 500 hrs	ASTM D-4355	70%	70%
<b>HYDRAULIC</b>			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	30 US Std. Sieve	0.600 mm
Permittivity	ASTM D-4491	0.05 sec <sup>-1</sup>	0.05 sec <sup>-1</sup>
<b>ROLL SIZES<sup>4</sup></b>		15.0 ft x 300 ft	4.6 m x 91.5 m

**NOTES:**

1. The property values listed above are effective 12/17/2018 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Values represent testing at time of manufacture.
3. Maximum average roll value.
4. Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.